

Record 11: JP8041253A**(ENG) POLYETHYLENE RESIN COMPOSITION****Assignee:** TOSOH CORP

[no drawing available]

Inventor(s): TSURUTA MEIJI ; OHAMA TOSHIO ;
MORIDERA YOSHIHIRO**Application No:** JP 17394094 A**Filing Date:** 19940726**Issue/Publication Date:** 19960213

Abstract: (ENG) <sec>PURPOSE: To obtain the composition, comprising a polymer mixture consisting essentially of a specific ethylene/hexene-1 copolymer, excellent in low stickiness and balance between transparency and tear strength and useful as packaging films, etc. CONSTITUTION: This composition is obtained by mixing (A) a principal component which is an ethylene/hexene-1 copolymer (EH), having 0.001-100g/10min melt flow rate(MFR), 0.86-0.94 g/cm³ density and ≤ 3 molecular weight distribution (Mw/Mn) and satisfying the relationship of formula I (T_m is the peak temperature of an endothermic curve; SCB is the number of short chains based on 1000 number of carbon atoms) with (B) the EH, having a density different from that of the component (A) and satisfying the MFR, density and Mw/Mn thereof and the relationship of formula I, the EH, having a higher density than that of the component (A), satisfying the MFR thereof and the relationship of formula I and further having ≥ 0.915 g/cm³ density or a high-density PE satisfying the MFR of the component (A). Furthermore, the composition satisfies the relationships of formula II (T_{mix} is the Elmendorf tear strength of the composition; d_{mix} is the density of the composition) and formula III (H_{mix} is the haze of the composition).</sec>

Priority Data: JP 17394094 19940726 A X;**IPC (International Class):** C08L02304; C08L02304; C08L02320